



Français

## Condat digital silk RL

Couché 2 Faces Brillant. Impression numérique. Bobines

| Propriété         |           |            | Unité            | Tolérance |           |            |            |            |            |            |            |            |            |  |  |  |
|-------------------|-----------|------------|------------------|-----------|-----------|------------|------------|------------|------------|------------|------------|------------|------------|--|--|--|
| Grammage          | ISO 536   | TAPPI T410 | g/m <sup>2</sup> | ± 4%      | <b>90</b> | <b>100</b> | <b>115</b> | <b>135</b> | <b>150</b> | <b>170</b> | <b>200</b> | <b>225</b> | <b>250</b> |  |  |  |
| Épaisseur         | ISO 534   | TAPPI T411 | µm               | ± 4%      | 80        | 89         | 105        | 119        | 135        | 159        | 200        | 225        | 243        |  |  |  |
| Blancheur CIE W   | ISO 11475 |            | %                | ± 3       | 121.0     | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      |  |  |  |
| Opacité           | ISO 2471  | TAPPI T519 | %                | -2.0      | 92.5      | 93.5       | 95.0       | 96.0       | 97.0       | 98.0       | -          | -          | -          |  |  |  |
| Lissé Bekk        | ISO 5627  | TAPPI T475 | s                |           | 210       | 200        | 180        | 220        | 180        | 160        | 120        | 110        | 250        |  |  |  |
| Humidité relative |           | TAPPI T502 | %                | ± 7%      | 40        | 40         | 40         | 40         | 40         | 40         | 40         | 40         | 40         |  |  |  |

- Dernière actualisation: **07-05-10**
- Ces valeurs sont sujettes à modification sans avis préalable

English

## Condat digital silk RL

Coated Paper 2 Sides Gloss. Digital Printing. Reels

| Property          |           |            | Unit | Tolerance |           |            |            |            |            |            |            |            |            |  |  |  |
|-------------------|-----------|------------|------|-----------|-----------|------------|------------|------------|------------|------------|------------|------------|------------|--|--|--|
| Substance         | ISO 536   | TAPPI T410 | gsm  | ± 4%      | <b>90</b> | <b>100</b> | <b>115</b> | <b>135</b> | <b>150</b> | <b>170</b> | <b>200</b> | <b>225</b> | <b>250</b> |  |  |  |
| Thickness         | ISO 534   | TAPPI T411 | µm   | ± 4%      | 80        | 89         | 105        | 119        | 135        | 159        | 200        | 225        | 243        |  |  |  |
| Whiteness CIE     | ISO 11475 |            | %    | ± 3       | 121.0     | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      |  |  |  |
| Opacity           | ISO 2471  | TAPPI T519 | %    | -2.0      | 92.5      | 93.5       | 95.0       | 96.0       | 97.0       | 98.0       | -          | -          | -          |  |  |  |
| Smoothness Bekk   | ISO 5627  | TAPPI T475 | s    |           | 210       | 200        | 180        | 220        | 180        | 160        | 120        | 110        | 250        |  |  |  |
| Relative Humidity |           | TAPPI T502 | %    | ± 7%      | 40        | 40         | 40         | 40         | 40         | 40         | 40         | 40         | 40         |  |  |  |

- Last updated: **07-05-10**
- Values are subject to change without notice.

Castellano

## Condat digital silk RL

Estucado 2 Caras Brillante. Impresión Digital. Bobinas

| Propiedad        |           |            | Unidad           | Tolerancia |           |            |            |            |            |            |            |            |            |  |  |  |
|------------------|-----------|------------|------------------|------------|-----------|------------|------------|------------|------------|------------|------------|------------|------------|--|--|--|
| Gramaje          | ISO 536   | TAPPI T410 | g/m <sup>2</sup> | ± 4%       | <b>90</b> | <b>100</b> | <b>115</b> | <b>135</b> | <b>150</b> | <b>170</b> | <b>200</b> | <b>225</b> | <b>250</b> |  |  |  |
| Calibre          | ISO 534   | TAPPI T411 | µm               | ± 4%       | 80        | 89         | 105        | 119        | 135        | 159        | 200        | 225        | 243        |  |  |  |
| Blancura CIE     | ISO 11475 |            | %                | ± 3        | 121.0     | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      |  |  |  |
| Opacidad         | ISO 2471  | TAPPI T519 | %                | -2.0       | 92.5      | 93.5       | 95.0       | 96.0       | 97.0       | 98.0       | -          | -          | -          |  |  |  |
| Lisura Bekk      | ISO 5627  | TAPPI T475 | s                |            | 210       | 200        | 180        | 220        | 180        | 160        | 120        | 110        | 250        |  |  |  |
| Humedad relativa |           | TAPPI T502 | %                | ± 7%       | 40        | 40         | 40         | 40         | 40         | 40         | 40         | 40         | 40         |  |  |  |

- Última actualización: **07-05-10**
- Los valores están sujetos a cambio sin aviso previo.

Português

## Condat digital silk RL

Couché 2 Faces Brilhante. Impressão Digital. Bobinas

| Propriedade       |           |            | Unidade | Tolerância |           |            |            |            |            |            |            |            |            |  |  |  |
|-------------------|-----------|------------|---------|------------|-----------|------------|------------|------------|------------|------------|------------|------------|------------|--|--|--|
| Gramagem          | ISO 536   | TAPPI T410 | gsm     | ± 4%       | <b>90</b> | <b>100</b> | <b>115</b> | <b>135</b> | <b>150</b> | <b>170</b> | <b>200</b> | <b>225</b> | <b>250</b> |  |  |  |
| Calibre           | ISO 534   | TAPPI T411 | µm      | ± 4%       | 80        | 89         | 105        | 119        | 135        | 159        | 200        | 225        | 243        |  |  |  |
| Brancura CIE      | ISO 11475 |            | %       | ± 3        | 121.0     | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      |  |  |  |
| Opacidade         | ISO 2471  | TAPPI T519 | %       | -2.0       | 92.5      | 93.5       | 95.0       | 96.0       | 97.0       | 98.0       | -          | -          | -          |  |  |  |
| Lisura Bekk       | ISO 5627  | TAPPI T475 | s       |            | 210       | 200        | 180        | 220        | 180        | 160        | 120        | 110        | 250        |  |  |  |
| Humidade relativa |           | TAPPI T502 | %       | ± 7%       | 40        | 40         | 40         | 40         | 40         | 40         | 40         | 40         | 40         |  |  |  |

- Última actualização: **07-05-10**
- Os valores estão sujeitos a mudanças sem pré-aviso.

Deutsch

## Condat digital silk RL

2-seitig Gestrichen Glänzend. Digitaldruckpapier. Rollen

| Kennzeichen           |           |            | Masseinheit      | Toleranz |           |            |            |            |            |            |            |            |            |  |  |  |
|-----------------------|-----------|------------|------------------|----------|-----------|------------|------------|------------|------------|------------|------------|------------|------------|--|--|--|
| Grammatur             | ISO 536   | TAPPI T410 | g/m <sup>2</sup> | ± 4%     | <b>90</b> | <b>100</b> | <b>115</b> | <b>135</b> | <b>150</b> | <b>170</b> | <b>200</b> | <b>225</b> | <b>250</b> |  |  |  |
| Dicke                 | ISO 534   | TAPPI T411 | µm               | ± 4%     | 80        | 89         | 105        | 119        | 135        | 159        | 200        | 225        | 243        |  |  |  |
| Weisse CIE            | ISO 11475 |            | %                | ± 3      | 121.0     | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      | 121.0      |  |  |  |
| Opazität              | ISO 2471  | TAPPI T519 | %                | -2.0     | 92.5      | 93.5       | 95.0       | 96.0       | 97.0       | 98.0       | -          | -          | -          |  |  |  |
| Bekk                  | ISO 5627  | TAPPI T475 | s                |          | 210       | 200        | 180        | 220        | 180        | 160        | 120        | 110        | 250        |  |  |  |
| Relative Feuchtigkeit |           | TAPPI T502 | %                | ± 7%     | 40        | 40         | 40         | 40         | 40         | 40         | 40         | 40         | 40         |  |  |  |

- Letzte Änderung: **07-05-10**
- Diese Werte können ohne vorherige Ankündigung geändert werden