



Français

Condat digital silk RL

Couché 2 Faces Demi-mat. Impression numérique. Bobines

Propriété			Unité	Tolérance												
Grammage	ISO 536	TAPPI T410	g/m ²	± 4%	90	100	115	135	150	170	200	225	250			
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	80	89	105	119	135	159	200	225	243			
Blancheur CIE W	ISO 11475		%	± 3	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0			
Opacité	ISO 2471	TAPPI T519	%	-2.0	92.5	93.5	95.0	96.0	97.0	98.0	-	-	-			
Lissé Bekk	ISO 5627	TAPPI T475	s		210	200	180	220	180	160	120	110	250			
Humidité relative		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40	40			

- Dernière actualisation: **03-05-11**
- Ces valeurs sont sujettes à modification sans avis préalable

English

Condat digital silk RL

Coated Paper 2 Sides Silk. Digital Printing. Reels

Property			Unit	Tolerance												
Substance	ISO 536	TAPPI T410	gsm	± 4%	90	100	115	135	150	170	200	225	250			
Thickness	ISO 534	TAPPI T411	µm	± 4%	80	89	105	119	135	159	200	225	243			
Whiteness CIE	ISO 11475		%	± 3	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0			
Opacity	ISO 2471	TAPPI T519	%	-2.0	92.5	93.5	95.0	96.0	97.0	98.0	-	-	-			
Smoothness Bekk	ISO 5627	TAPPI T475	s		210	200	180	220	180	160	120	110	250			
Relative Humidity		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40	40			

- Last updated: **03-05-11**
- Values are subject to change without notice.

Castellano

Condat digital silk RL

Estucado 2 Caras Semimate. Impresión Digital. Bobinas

Propiedad			Unidad	Tolerancia												
Gramaje	ISO 536	TAPPI T410	g/m ²	± 4%	90	100	115	135	150	170	200	225	250			
Calibre	ISO 534	TAPPI T411	µm	± 4%	80	89	105	119	135	159	200	225	243			
Blancura CIE	ISO 11475		%	± 3	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0			
Opacidad	ISO 2471	TAPPI T519	%	-2.0	92.5	93.5	95.0	96.0	97.0	98.0	-	-	-			
Lisura Bekk	ISO 5627	TAPPI T475	s		210	200	180	220	180	160	120	110	250			
Humedad relativa		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40	40			

- Última actualización: **03-05-11**
- Los valores están sujetos a cambio sin aviso previo.

Português

Condat digital silk RL

Couché 2 Faces Semi-mate. Impressão Digital. Bobinas

Propriedade			Unidade	Tolerância												
Gramagem	ISO 536	TAPPI T410	gsm	± 4%	90	100	115	135	150	170	200	225	250			
Calibre	ISO 534	TAPPI T411	µm	± 4%	80	89	105	119	135	159	200	225	243			
Brancura CIE	ISO 11475		%	± 3	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0			
Opacidade	ISO 2471	TAPPI T519	%	-2.0	92.5	93.5	95.0	96.0	97.0	98.0	-	-	-			
Lisura Bekk	ISO 5627	TAPPI T475	s		210	200	180	220	180	160	120	110	250			
Humidade relativa		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40	40			

- Última actualização: **03-05-11**
- Os valores estão sujeitos a mudanças sem pré-aviso.

Deutsch

Condat digital silk RL

2-seitig Gestrichen Satiniert. Digitaldruckpapier. Rollen

Kennzeichen			Masseinheit	Toleranz												
Grammatur	ISO 536	TAPPI T410	g/m ²	± 4%	90	100	115	135	150	170	200	225	250			
Dicke	ISO 534	TAPPI T411	µm	± 4%	80	89	105	119	135	159	200	225	243			
Weisse CIE	ISO 11475		%	± 3	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0			
Opazität	ISO 2471	TAPPI T519	%	-2.0	92.5	93.5	95.0	96.0	97.0	98.0	-	-	-			
Bekk	ISO 5627	TAPPI T475	s		210	200	180	220	180	160	120	110	250			
Relative Feuchtigkeit		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40	40			

- Letzte Änderung: **03-05-11**
- Diese Werte können ohne vorherige Ankündigung geändert werden