

Condat gloss

Coated Paper 2 Sides Gloss

Property			Units	Tolerance	Text				Cover						
					60#	70#	80#	100#	80#	93#	100#	110#	130#	140#	148#
Substance	ISO 536	TAPPI T410	gsm	± 4%	89	104	118	148	216	251	270	297	351	378	400
Thickness (pt.)	ISO 534	TAPPI T411	pt.	± 7%	2,8	3,2	3,6	4,5	7,0	7,5	9,0	9,1	11,2	12,4	13,1
Thickness (µm)	ISO 534	TAPPI T411	µm	± 7%	70	81	92	115	178	191	229	230	285	315	332
Brightness R457	ISO 2470-2		%	± 2	94	94	94	95	95,2	95,2	95,2	95,2	95,2	96	96
Whiteness CIE D65 /10°	ISO 11475		%	±3	119	119	119	122	122	122	122	122	122	122	122
Opacity	ISO 2471	TAPPI T519	%	-2	89,5	93,5	95,0	96,0	-	-	-	-	-	-	-
Paper Gloss	ISO 8254-1	TAPPI T480	%	±5	66	67	68	70	70	74	74	74	74	77	77
Smoothness Bekk	ISO 5627	TAPPI T475	sec	ref	1200	1100	950	700	500	400	300	300	250	250	250
Relative Humidity	TAPPI 502		%	± 10pts	48	48	48	48	48	48	48	48	48	50	50

- Last updated: **06-05-11**
- Values are subject to change without notice.