

## Condat matt Périgord

Coated Paper 2 Sides Bulky Matt

Property		Unit	Tolerance	Text				Cover				
				60#	70#	80#	100#	80#	93#	100#	110#	130#
Substance	ISO 536 TAPPI T410	gsm	± 4%	89	104	118	148	216	251	270	297	351
Thickness (pt.)	ISO 534 TAPPI T411	pt.	± 4%	3,7	4,1	4,8	6,1	9,3	10,4	11,7	12,9	15,4
Thickness (µm)	ISO 534 TAPPI T411	µm	± 4%	93	104	123	156	236	265	297	327	392
Brightness R457	ISO 2470-2 -	%	± 2	96	96	96	97	97	97	97	97	97
Whiteness CIE D65 /10°	ISO 11475 -	%	± 3	121.4	121.4	121.4	121.4	121.6	121.6	121.6	121.6	121.6
Opacity	ISO 2471 TAPPI T519	%	-2.0	93.0	94.5	96.0	97.5	-	-	-	-	-
Roughness Bendtsen	ISO 8791-2 -	ml/min	≤100	100	100	100	-	-	-	-	-	-
Smoothness Bekk	ISO 5627 TAPPI T475	s		-	-	-	100	210	210	210	210	190
Relative Humidity	- TAPPI T502	%	± 10%	50	50	50	50	50	50	50	50	50

- Last updated: **07-09-11**
- Values are subject to change without notice.