

## Condat silk Roto

Impression Roto-Offset / Bobines. Couché 2 Faces Demi-mat

Propriété			Unité	Tolérance	90	100	110	115	130	135	150	170	200	225
Grammage	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	90	100	110	115	130	135	150	170	200	225
Épaisseur	ISO 534	TAPPI T411	µm	± 4%	80	89	99	105	113	119	135	159	200	225
Blancheur CIE W	ISO 11475		%	± 3	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0
Opacité	ISO 2471	TAPPI T519	%	-2.0	92.5	93.5	94.5	95.0	95.5	96.0	97.0	98.0	-	-
Lissé Bekk	ISO 5627	TAPPI T475	s		210	200	180	180	220	220	180	160	120	110
Humidité relative		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40	40	40

- Dernière actualisation: **07-05-10**
- Ces valeurs sont sujettes à modification sans avis préalable

## Condat silk Roto

Heat Set Web Offset / Reels. Coated Paper 2 Sides Silk

Property			Unit	Tolerance	90	100	110	115	130	135	150	170	200	225
Substance	ISO 536	TAPPI T410	gsm	± 4%	90	100	110	115	130	135	150	170	200	225
Thickness	ISO 534	TAPPI T411	µm	± 4%	80	89	99	105	113	119	135	159	200	225
Whiteness CIE	ISO 11475		%	± 3	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0
Opacity	ISO 2471	TAPPI T519	%	-2.0	92.5	93.5	94.5	95.0	95.5	96.0	97.0	98.0	-	-
Smoothness Bekk	ISO 5627	TAPPI T475	s		210	200	180	180	220	220	180	160	120	110
Relative Humidity		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40	40	40

- Last updated: **07-05-10**
- Values are subject to change without notice.

## Condat silk Roto

Impresión Roto-Offset / Bobinas. Estucado 2 Caras Semimate

Propiedad			Unidad	Tolerancia	90	100	110	115	130	135	150	170	200	225
Gramaje	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	90	100	110	115	130	135	150	170	200	225
Calibre	ISO 534	TAPPI T411	µm	± 4%	80	89	99	105	113	119	135	159	200	225
Blancura CIE	ISO 11475		%	± 3	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0
Opacidad	ISO 2471	TAPPI T519	%	-2.0	92.5	93.5	94.5	95.0	95.5	96.0	97.0	98.0	-	-
Lisura Bekk	ISO 5627	TAPPI T475	s		210	200	180	180	220	220	180	160	120	110
Humedad relativa		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40	40	40

- Última actualización: **07-05-10**
- Los valores están sujetos a cambio sin aviso previo.

## Condat silk Roto

Impressão Roto-Offset / Bobinas. Couché 2 Faces Semi-mate

Propriedade			Unidade	Tolerância	90	100	110	115	130	135	150	170	200	225
Gramagem	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	90	100	110	115	130	135	150	170	200	225
Calibre	ISO 534	TAPPI T411	µm	± 4%	80	89	99	105	113	119	135	159	200	225
Brancura CIE	ISO 11475		%	± 3	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0
Opacidade	ISO 2471	TAPPI T519	%	-2.0	92.5	93.5	94.5	95.0	95.5	96.0	97.0	98.0	-	-
Lisura Bekk	ISO 5627	TAPPI T475	s		210	200	180	180	220	220	180	160	120	110
Humidade relativa		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40	40	40

- Última atualização: **07-05-10**
- Os valores estão sujeitos a mudanças sem pré-aviso.

## Condat silk Roto

Roto-Offsetdruck / Rollen. 2-seitig Gestrichen Matt Satiniertes

Kennzeichen			Masseinheit	Toleranz	90	100	110	115	130	135	150	170	200	225
Grammatur	ISO 536	TAPPI T410	g/m <sup>2</sup>	± 4%	90	100	110	115	130	135	150	170	200	225
Dicke	ISO 534	TAPPI T411	µm	± 4%	80	89	99	105	113	119	135	159	200	225
Weisse CIE	ISO 11475		%	± 3	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0	121.0
Opazität	ISO 2471	TAPPI T519	%	-2.0	92.5	93.5	94.5	95.0	95.5	96.0	97.0	98.0	-	-
Bekk	ISO 5627	TAPPI T475	s		210	200	180	180	220	220	180	160	120	110
Relative Feuchtigkeit		TAPPI T502	%	± 7%	40	40	40	40	40	40	40	40	40	40

- Letzte Änderung: **07-05-10**
- Diese Werte können ohne vorherige Ankündigung geändert werden