



(USA)

**Condat silk**

Coated Paper 2 Sides Silk

Property	ISO 536	TAPPI T410	Units	Tolerance	Text				Cover						
					60#	70#	80#	100#	80#	93#	100#	110#	130#	140#	148#
Substance	ISO 536	TAPPI T410	gsm	± 4%	89	104	118	148	216	251	270	297	351	378	400
Thickness (pt.)	ISO 534	TAPPI T411	pt.	± 7%	3,1	3,5	4,0	5,2	8,0	9,4	10,3	11,6	14,1	15,7	16,5
Thickness (µm)	ISO 534	TAPPI T411	µm	± 7%	78	90	102	133	203	240	262	295	358	400	420
Brightness R457	ISO 2470-2		%	± 2	96	96	96	96	95,6	95,6	95,6	95,6	95,6	96,5	96,5
Whiteness CIE D65 /10°	ISO 11475		%	±3	120	120	120	120	120	120	120	120	120	121	121
Opacity	ISO 2471	TAPPI T519	%	-2	91,5	93,5	95,0	97,0	-	-	-	-	-	-	-
Smoothness Bekk	ISO 5627	TAPPI T475	sec	ref	300	300	300	250	100	100	90	90	90	200	160
Relative Humidity	TAPPI 502		%	± 10pts	48	48	48	48	48	48	48	48	48	48	50

- Last updated: **06-05-11**
- Values are subject to change without notice.