



(USA)

Condat Silk

Coated Paper 2 Sides Silk

Property		Units	Tolerance	Text			Cover		
				70#	80#	100#	80#	100#	130#
B.W.	ISO 536	lb	± 4%						
Caliper	TAPPI 411	pt.	± 7%	3,6	4,1	5,4	8,5	11,1	14,6
Opacity	TAPPI 519	%	±2pts	93,5	95,5	98	-	-	-
Paper Gloss	TAPPI 480	%	± 5pts	35	35	35	35	35	35
Smoothness Bekk	ISO 5627	sec	ref	220	220	200	270	250	230
Brightness	TAPPI 525	Index	± 2pts	92	92	92	92	92	92
Whiteness CIE D65 /10°	ISO 11475	Index	±3pts	121	121	121	121	121	121
Relative Humidity	TAPPI 502	%	± 10pts	50	50	50	50	50	50

- Last updated: **30-01-09**
- Values are subject to change without notice.