

Property	ISO	TAPPI	Units	Tolerance	Text					Cover						
					60#	70#	80#	100#	115#	80#	93#	100#	110#	130#	140#	148#
Substance	ISO 536	TAPPI T410	gsm	± 4%	89	104	118	148	170	216	251	270	297	351	378	400
Thickness (pt.)	ISO 534	TAPPI T411	pt.	± 4%	3,1	3,5	4,0	5,2	6,1	8,0	9,4	10,3	11,6	14,1	15,7	16,5
Thickness (µm)	ISO 534	TAPPI T411	µm	± 4%	78	90	102	133	156	203	240	262	295	358	400	420
Brightness R457	ISO 2470-2	-	%	± 2	96	96	96	96,5	96,5	95,6	95,6	95,6	95,6	95,6	96,5	96,5
Whiteness CIE D65 /10°	ISO 11475	-	%	±3	119	119	119	120	120	120	120	120	120	120	121	121
Opacity	ISO 2471	TAPPI T519	%	-2	91,5	93,5	95,0	97,0	98,0	-	-	-	-	-	-	-
Smoothness Bekk	ISO 5627	TAPPI T475	sec	ref	300	300	300	200	170	100	100	90	90	90	200	160
Relative Humidity	-	TAPPI 502	%	± 10pts	48	48	48	48	48	48	48	48	48	48	50	50

- Last updated: **07-09-11**
- Values are subject to change without notice.